



**Technical Data Sheet
SBR 60A Black**

Property	Rating or Value
Tensile, PSI	2250
Modulus, 300%	1500
Hardness, Shore A	60
Elongation, %	465
Specific Gravity	1.18
Chemical Resistance	Average
Max Service Temperature (deg F)	220

Above values are typical and to be used as a guide only. They are not intended to be used for engineering specifications. End user must test in their application to determine suitability.